



EH: Hot Melt Polyester Resins

Resin Selector and FDA Reference Guides

Resin Selector Guide

Grade	IV	TG- celsius	FDA	Form
EH-100	0.73	-7		Pellets
EH-101	0.73	-1		Pellets
EH-105	0.66	-11		Pellets
EH-400	0.64	25		Pellets
EH-401	0.65	27		Pellets
EH-500	0.63	21	✓	Pellets
EH-501	0.61	2		Pellets
EH-550	0.7	23	✓	Pellets
EH-601	0.76	16		Pellets
EH-602	0.9	-32		Pellets
EH-603	0.9	-30		Pellets
EH-700	0.59	14		Pellets
EH-505	0.55	0		Pellets
EH-102	0.86	-		Pellets
EH-1100	0.81	-		Pellets
EH-1000	0.64	-		Pellets



FDA Reference Guide

Key	
✓	Yes
✓	Restrictions apply. A case by case review of the regulation is required. Call with inquiries.
✓	FCN

Grade	175.105	175.3	175.32	176.17	176.18	177.121	177.139	177.1395	177.163
EH-100	✓	✓		✓	✓	✓	✓	✓	
EH-101	✓	✓		✓	✓	✓	✓	✓	
EH-105	✓	✓		✓	✓	✓	✓	✓	
EH-400	✓	✓		✓	✓	✓	✓	✓	
EH-401	✓	✓		✓	✓	✓	✓	✓	
EH-500	✓	✓		✓	✓	✓	✓	✓	
EH-501	✓	✓		✓	✓	✓	✓	✓	
EH-550	✓	✓		✓	✓	✓	✓	✓	
EH-601	✓	✓		✓	✓	✓	✓	✓	
EH-602	✓	✓		✓	✓	✓	✓	✓	
EH-603	✓	✓		✓	✓	✓	✓	✓	
EH-700	✓	✓		✓	✓	✓	✓	✓	