



EW: Water-Borne Polyester Resins

Resin Selector and FDA Reference Guides

Resin Selector Guide

Grade	IV	TG- celsius	FDA	Form
EW-100R	0.45	44		Pellet
EW-100G	0.44	47		Pellet
EW-100Q	0.42	44		Pellet
EW-100D	0.23	52		Flake
EW-210	0.35	57		Flake
EW-300	0.3	36		Pellet
EW-312	0.45	58	✓	Pellet
EW-370	0.14	43	✓	Pellet
EW-730	0.53	-25		Sheet
EW-100(G)	0.44	44		



FDA Reference Guide

Key	
✓	Yes
✓	Restrictions apply. A case by case review of the regulation is required. Call with inquiries.
✓	Limited to non-alcoholic foods
✓	FCN

Grade	175.105	175.3	175.32	176.17	176.18	177.121	177.139	177.1395	177.163
EW-100R	✓	✓	✓		✓	✓	✓	✓	
EW-100G	✓	✓	✓		✓	✓	✓	✓	
EW-100Q	✓	✓	✓		✓	✓	✓	✓	
EW-100D	✓	✓	✓		✓	✓	✓	✓	
EW-210	✓	✓	✓		✓	✓	✓	✓	
EW-300	✓	✓	✓		✓	✓	✓	✓	
EW-312	✓	✓	✓		✓	✓	✓	✓	
EW-370	✓	✓	✓		✓	✓	✓	✓	
EW-730	✓	✓	✓		✓	✓	✓	✓	